

Please amend the application as set forth below.

In the Claims:

1. (Currently Amended) A film for forming a vapor deposited balloon, which comprises a five-layer structure composed of a polyamide resin layer, a polyolefin layer, a polyamide resin layer, an adhesive resin layer and a seal layer, the five layers being disposed in the order recited, wherein the film is stretched in [the] a machine direction using a roll stretching machine and in [the] a transverse direction using a tenter stretching machine, and [has] said film having a thickness of about 15 to 35 μ m, wherein the polyamide resin layers comprise about 70-[97]95 wt. % of ~~crystalline~~ nylon 6 and about 30-5 wt. % of amorphous nylon, and wherein haze of the film ranges from 1.0% to 7.0%.
2. (Original) The film for forming a vapor deposited balloon according to claim 1 wherein the polyamide resin layer is mixed resin layer comprising 5 to 30 wt. % of an amorphous polyamide resin and/or a semiaromatic polyamide resin
3. (Original) A film for forming a vapor deposited balloon, which is produced by forming a metal deposited layer over the whole or partial surface of the outermost polyamide resin layer of the film according to claim 1.
4. (Previously Presented) A film for forming a vapor deposited balloon, which has a transparent appearance on one side and comprises a metal deposited layer formed on the other side, wherein the metal deposited layer is formed on the surface of the outermost polyamide resin layer of the film as defined in claim 1.
5. (Original) A balloon comprising the film for forming a vapor deposited balloon according to claim 1.

6. (Cancelled)